



MOL Plc.
DS MOL

MOL_0812_033 / 3

FR DMWF 6266

Printed: 5/28/2020

SAP product number		13008370	
Combined Nomenclature			
Property	Unit	Standard	Requirement
Dropping Point	C_fok	ASTM D 3954	62.0 - 66.0
Penetration at 25 °C	dmm	ASTM D 1321	12 - 20
Viscosity at 100 °C	mm ² /s	ISO 3104	5.40 - 6.50
Oil Content	%(m/m)	ASTM D 721	max. 1.50
Saybolt Color		ASTM D 156	min. 18
Odour		ASTM D 1833	max. 1
Absorption to 280-289 nm	Abs	FDA 172886	max. 0.15
Absorption to 290-299 nm	Abs	FDA 172886	max. 0.12
Absorption to 300-359 nm	Abs	FDA 172886	max. 0.08
Absorption to 360-400 nm	Abs	FDA 172886	max. 0.02

Remark :