



MOL Plc.
DS MOL

MOL_0812_003 / 9

FR DWC 5658

RAL_GZ_041:2016

Printed: 5/28/2020

SAP product number		13000471	
Combined Nomenclature			
Property	Unit	Standard	Requirement
Melting Point	C_fok	ASTM D 87	56.0 - 58.0
Penetration at 25 °C	dmm	ASTM D 1321	max. 20
Oil Content	%(m/m)	ASTM D 721	max. 0.50
Saybolt Color		ASTM D 156	min. 26
Sulphur content	mg/kg	ASTM D 2622	max. 20
Odour		ASTM D 1833	max. 1
Ash content	%(m/m)	ISO 6245	max. 0.0500
Paraffin PAH		Ph.Eur.4-4_2.2.25	Adequate
Benzene	mg/kg	In-house method	max. 0.50
Toluene	mg/kg	In-house method	max. 1.00
Xylene	mg/kg	In-house method	max. 1.0
UV stability		RAL_GZ_041	min. 15
Lead content	mg/kg	ICP	max. 0.20

Remark :