



MOL Plc.
DS MOL

MOL_0852_003 / 5

FR DWC 5759

Printed: 5/28/2020

SAP product number		13000360	
Combined Nomenclature			
Property	Unit	Standard	Requirement
Melting point	C_fok	ISO 3841	57.0 - 59.0
Oil Content	%(m/m)	ASTM D 721	max. 0.75
Viscosity at 100 °C	mm ² /s	ISO 3104	3.80 - 4.40
Penetration at 25 °C	dmm	ASTM D 1321	12 - 17
Penetration at 40 °C	dmm	ASTM D 1321	Report
Saybolt Color		ASTM D 156	min. 24
Sulphur content	mg/kg	ASTM D 2622	max. 20
Odour		ASTM D 1833	max. 1
Ash content	%(m/m)	ISO 6245	max. 0.050
Paraffin PAH		Ph.Eur.4-4_2.2.25	Adequate
Benzene	mg/kg	In-house method	max. 0.50
Toluene	mg/kg	In-house method	max. 1.00
Xylene	mg/kg	In-house method	max. 1

Remark :