



MOL Plc.
DS MOL

MOL_0812_004 / 9

FR DWC 5860

RAL_GZ_041:2016

Printed: 5/28/2020

| SAP product number | | 13000481 | |
|-----------------------|--------|-------------------|-------------|
| Combined Nomenclature | | | |
| Property | Unit | Standard | Requirement |
| Melting Point | C_fok | ASTM D 87 | 58.0 - 60.0 |
| Penetration at 25 °C | dmm | ASTM D 1321 | max. 20 |
| Oil Content | %(m/m) | ASTM D 721 | max. 0.50 |
| Saybolt Color | | ASTM D 156 | min. 26 |
| Sulphur content | mg/kg | ASTM D 2622 | max. 20 |
| Odour | | ASTM D 1833 | max. 1 |
| Ash content | %(m/m) | ISO 6245 | max. 0.0500 |
| Paraffin PAH | | Ph.Eur.4-4_2.2.25 | Adequate |
| Benzene | mg/kg | In-house method | max. 0.50 |
| Toluene | mg/kg | In-house method | max. 1.00 |
| Xylene | mg/kg | In-house method | max. 1 |
| UV stability | | RAL_GZ_041 | min. 15 |
| Lead content | mg/kg | ICP | max. 0.20 |

Remark :