



MOL Plc.  
DS MOL

# MOL\_0812\_027 / 3

FR DWC-EX 5456

Printed: 5/28/2020

SAP product number		13008355	
Combined Nomenclature			
Property	Unit	Standard	Requirement
Melting Point	C_fok	ASTM D 87	54.0 - 56.0
Penetration at 25 °C	dmm	ASTM D 1321	max. 20
Oil Content	%(m/m)	ASTM D 721	max. 0.50
Saybolt Color		ASTM D 156	min. 26
Sulphur content	mg/kg	ASTM D 2622	max. 20
Odour		ASTM D 1833	max. 1
Ash content	%(m/m)	ISO 6245	max. 0.0500
Water Soluble Acid and Base		Ph.Eur. 4-4	Not detected
Absorption to 280-289 nm	Abs	FDA 172886	max. 0.15
Absorption to 290-299 nm	Abs	FDA 172886	max. 0.12
Absorption to 300-359 nm	Abs	FDA 172886	max. 0.08
Absorption to 360-400 nm	Abs	FDA 172886	max. 0.02
Paraffin PAH		Ph.Eur.4-4_2.2.25	Adequate
Benzene	mg/kg	In-house method	max. 0.5
Toluene	mg/kg	In-house method	max. 1.00
Xylene	mg/kg	In-house method	max. 1.00
UV stability		RAL_GZ_041	min. 15

Remark :