



MOL Plc.
DS MOL

MOL_1021_005 / 1
Building Industry Bitumen EB 85/25
MSZ EN 13304

Printed:
11/27/2018

SAP product number		12000145	
Combined Nomenclature			
Property	Unit	Standard	Requirement
Appearance		Visual appearance	Homogeneous
Penetration at 25 °C	dmm	MSZ EN 1426	20 - 30
Softening Point	C_fok	MSZ EN 1427	80.0 - 90.0
Breaking Point	C_fok	MSZ EN 12593	max. -10.0
Part of soluble in Toluene	%(m/m)	MSZ EN 12592	min. 99.00
Melegítés utáni tömegveszteség	%(m/m)	MSZ EN 13303	max. 0.50
Flash Point by Cleveland	C_fok	EN ISO 2592	min. 250

Remark :