



MOL Plc.
DS MOL

MOL_1021_006 / 1
Building Industry Bitumen EB 85/40
MSZ EN 13304

Printed:
11/27/2018

| SAP product number | | 12000146 | |
|--------------------------------|--------|-------------------|-------------|
| Combined Nomenclature | | | |
| Property | Unit | Standard | Requirement |
| Appearance | | Visual appearance | Homogeneous |
| Penetration at 25 °C | dmm | MSZ EN 1426 | 35 - 45 |
| Softening Point | C_fok | MSZ EN 1427 | 80.0 - 90.0 |
| Breaking Point | C_fok | MSZ EN 12593 | max. -15.0 |
| Part of soluble in Toluene | %(m/m) | MSZ EN 12592 | min. 99.00 |
| Melegítés utáni tömegveszteség | %(m/m) | MSZ EN 13303 | max. 0.50 |
| Flash Point by Cleveland | C_fok | EN ISO 2592 | min. 250 |

Remark :