



MOL Plc.
DS MOL

MOL_1031_012 / 1

Modified Bitumen 10/40-65

MSZ EN 14023 : 2010

Printed: 1/16/2019

SAP product number		12000714	
Combined Nomenclature			
Property	Unit	Standard	Requirement
Appearance		Visual appearance	Homogeneous
Density at 25 °C	g/cm3	MSZ EN ISO 3838	Report
Softening Point	C_fok	MSZ EN 1427	min. 65.0
Penetration at 25 °C	dmm	MSZ EN 1426	10 - 40
Breaking Point	C_fok	MSZ EN 12593	max. -10.0
Cohesion energy at 10 °C	J/cm2	MSZ EN 13703	min. 2
Change in mass at 163 °C	%(m/m)	MSZ EN 12607-1	max. 0.30
Residual Penetration	%	MSZ EN 12607-1	min. 50
Rising of Softening Point	C_fok	MSZ EN 12607-1	max. 8.0
Elastic Recovery at 25 °C	%	ÚT 2-3.503	min. 60.00
Softening Point difference	C_fok	MSZ EN 13399	max. 5.0
Flash Point by Cleveland	C_fok	EN ISO 2592	min. 250

Remark :