



MOL Plc.
DS MOL

MOL_1031_006 / 2

Modified Bitumen 25/55-65

MSZ EN 14023 : 2010

Printed: 1/16/2019

SAP product number		12000703	
Combined Nomenclature			
Property	Unit	Standard	Requirement
Appearance		Visual appearance	Homogeneous
Density at 25 °C	g/cm3	MSZ EN ISO 3838	Report
Penetration at 25 °C	dmm	MSZ EN 1426	25 - 55
Softening Point	C_fok	MSZ EN 1427	min. 65.0
Breaking Point	C_fok	MSZ EN 12593	max. -12
Cohesion energy at 10 °C	J/cm2	MSZ EN 13703	min. 2.00
Softening Point difference	C_fok	MSZ EN 13399	max. 5
Change in mass at 163 °C	%(m/m)	MSZ EN 12607-1	max. 0.5
Residual Penetration	%	MSZ EN 12607-1	min. 50
Rising of Softening Point	C_fok	MSZ EN 12607-1	max. 8.0
Flash Point by Cleveland	C_fok	EN ISO 2592	min. 250
Elastic Recovery at 25 °C	%	MSZ EN 13398	min. 80.00

Remark :