



MOL Plc.
DS MOL

MOL_1031_014 / 1
Útépítési modifikált bitumen 45/80-75 (ApolloBit-H)
MSZ EN 14023:2010

Printed:
11/27/2018

SAP product number		12000742	
Combined Nomenclature			
Property	Unit	Standard	Requirement
Appearance		Visual appearance	Homogeneous
Density at 25 °C	g/cm3	MSZ EN ISO 3838	Report
Penetration at 25 °C	dmm	MSZ EN 1426	45 - 80
Softening Point	C_fok	MSZ EN 1427	min. 75.0
Breaking Point	C_fok	MSZ EN 12593	max. -18.0
Cohesion energy at 5 °C	J/cm2	MSZ EN 13703	min. 3
Softening Point difference	C_fok	MSZ EN 13399	max. 5
Change in mass at 163 °C	%(m/m)	MSZ EN 12607-1	max. 0.30
Residual Penetration	%	MSZ EN 12607-1	min. 60
Rising of Softening Point	C_fok	MSZ EN 12607-1	max. 8.0
Flash Point by Cleveland	C_fok	EN ISO 2592	min. 250
Elastic Recovery at 25 °C	%	MSZ EN 13398	min. 70.00

Remark :