



MOL Plc.
DS MOL

MOL_1011_005 / 5

Paving grade Bitumen 20/30

MSZ EN 12591:2009

Printed:
11/27/2018

SAP product number		12000073	
Combined Nomenclature			
Property	Unit	Standard	Requirement
Density at 25 °C	g/cm ³	MSZ EN ISO 3838	Report
Penetration at 25 °C	dmm	MSZ EN 1426	20 - 30
Softening Point	C_fok	MSZ EN 1427	55.0 - 63.0
Viscosity at 135 °C	mm ² /s	MSZ EN 12595	min. 530.0
Change in mass at 163 °C	%(m/m)	MSZ EN 12607-1	max. 0.5
Residual Penetration	%	MSZ EN 12607-1	min. 55
Softening Point after RTFOT	C_fok	MSZ EN 12607-1	min. 57
Rising of Softening Point	C_fok	MSZ EN 12607-1	max. 8.0
Flash Point by Cleveland	C_fok	EN ISO 2592	min. 240
Part of soluble in Toluene	%(m/m)	MSZ EN 12592	min. 99.00

Remark :