



MOL Plc.
DS MOL

MOL_1011_002 / 3

Paving grade Bitumen 70/100

MSZ EN 12591:2009

Printed:
11/27/2018

SAP product number		12000108	
Combined Nomenclature			
Property	Unit	Standard	Requirement
Density at 25 °C	g/cm3	MSZ EN ISO 3838	Report
Appearance		Visual appearance	Homogeneous
Penetration at 25 °C	dmm	MSZ EN 1426	70 - 100
Softening Point	C_fok	MSZ EN 1427	43.0 - 51.0
Viscosity at 135 °C	mm2/s	MSZ EN 12595	min. 230.0
Breaking Point	C_fok	MSZ EN 12593	max. -10
Change in mass at 163 °C	%(m/m)	MSZ EN 12607-1	max. 0.80
Residual Penetration	%	MSZ EN 12607-1	min. 46
Softening Point after RTFOT	C_fok	MSZ EN 12607-1	min. 45
Rising of Softening Point	C_fok	MSZ EN 12607-1	max. 9.0
Flash Point by Cleveland	C_fok	EN ISO 2592	min. 230
Part of soluble in Toluene	%(m/m)	MSZ EN 12592	min. 99.00

Remark :